


PRODUCT DATA SHEET

Emcrete II by Emseal

Non-Hazardous High-Impact Elastomeric Concrete Material



Emcrete II expansion joint
patching and nosing material

Product Description

Emcrete II is a flexible, durable, high-impact elastomeric concrete material. It is a bio-based, non-hazardous, extremely-low VOC product primarily used as a component of an expansion joint assembly either to fill blockouts on each side of an expansion joint gap, to repair a damaged expansion joint gap edge, as an impact-absorbing backfill nosing, or as a fast curing patching material for potholes, or spalls on concrete roadways, bridges, sidewalks, etc.

Emcrete II is comprised of a two-component polyurethane resin mixed with sand and aggregates.

Uses and Applications

Typical use of Emcrete II applications include:

Elastomeric Concrete – To act as an elastomeric concrete where the possibility of spalling or cracking is a concern for standard concrete or where existing spalls or potholes in concrete roadways, bridges, sidewalks, etc. is required.

Repair – To repair spalled gap edges in high load-bearing applications. The spalled concrete must be cut out using industry standards for concrete repair. Once the gap edge has been cut and cleaned, the self-leveling Emcrete II can be poured to form a horizontal elastomeric gap edge that is more resistant to spalling and gap edge deterioration.

Features

- Trafficable surface
- Flexible impact resistant
- Compatible with extremes in temperatures
- Chemical resistant surfaces
- Wide range of adhesive applications
- Fast mixing and installation
- Affordable results

Installation Summary

Substrates must be thoroughly dry and the temperature must be at least 45°F (8°C) and rising to install Emcrete II. The bonding surface should be in sound and good condition before prepping. Newly poured concrete must be full cured. The entire bonding surface is to be wire brushed and fully cleaned leaving no contaminants such as dirt, dust, oils, or other residue on any surface. Next, the area where Emcrete II will be poured should be fully prepped and formed.

The substrate is then primed with Sikadur®-32 Hi-Mod primer (which is shipped in addition to units of Emcrete II). Emcrete II is then mixed in accordance with the complete Installation Instructions in the pre-measured amounts provided. Emcrete II is then poured into the forms where it will self-level and cure exothermically. It can be trowelled to ensure a consistent surface. The working time of Emcrete II is less than 10-minutes after mixing. Working time, and cure time, is longer in cool weather and shorter in hot weather.

Emcrete II reaches a hardness which allows forms to be pulled within 1 hour (temperatures between 60° - 80°F / 16° - 27°C). If Emcrete II is installed in greater than 80°F, forms can be pulled as quickly as 30-45 mins after mixing. If Emcrete II is to be used in conjunction with BEJS Joint System, forms can be pulled at 1 hr. and BEJS installed after light prep of the Emcrete II joint substrate.

Pedestrian & vehicular traffic (temperatures between 60° - 80°F / 16° - 27°C) Emcrete II can accept traffic within 2-hour after application.

Supply

Packaging – Emcrete II Elastomeric Concrete kit is comprised of:

Part A Liquid (0.96 Gal.) per unit

Part B Liquid (0.53 Gal.) per unit

Part C Aggregate (57.8 lb) per unit

Installation requires additional Sikadur®-32 Hi-Mod primer.

Kit Yield – 1 Unit = 0.6 cubic-feet / 2 Units = 1.2 cubic-feet

Storage – Components have a storage shelf life of 1-year at 65° - 90°F (19° - 33°C)

Physical Results

Physical Property	Test Method	Value
Compressive Strength	ASTM D695	Min. 2200 psi
Bond Strength to Concrete by Slant Shear	ASTM C882	Min. 1000 psi
Abrasion Index	ASTM C501	Max. 2%
Resilience	ASTM D695	Min. 99%
Durometer Hardness	ASTM D2240	Min. 65
Percent Elongation	ASTM D638	Min. 50%

CAD & CAD Guide Specs

Guide Specifications and CAD Details are available online at Emseal.com or by [contacting Sika Emseal](#).

Warranty

Standard or project-specific warranties are available from Sika Emseal on request. Each product can only perform its designed function if it, and the joint-gap into which it is installed, is sized to suit anticipated joint movements in consideration of the movement capability of the product and in consideration of the temperature at time of installation, and if it is installed in strict accordance with Sika Emseal's installation instructions.

Availability & Price

Emcrete II is available for shipment internationally. Prices are available from local representatives and/or directly from the manufacturer. The product range is continually being updated, and accordingly Watson Bowman Acme reserves the right to modify or withdraw any product without prior notice.

Emcrete II Applications

Figure 1: Emcrete II Used as Expansion Joint Nosing Material





Figure 2: Emcrete II Used as Concrete Patching Material



Watson Bowman Acme
 95 Pineview Dr.
 Amherst, NY 14228 USA
 Phone: 716.691.7566
 Fax: 716.691.9239

www.watsonbowmanacme.com

SIKA CORPORATION
 201 Polito Avenue
 Lyndhurst, NJ 07071 USA
 Phone: +1-800-933-7452
 Fax: +1-2019336225

www.usa.sika.com

Product Data Sheet
 Emcrete II by Emseal
 October 2023



BUILDING TRUST

